



HD7200B

High Density Polyethylene Resin

Special Characteristics: InnoPlus HD7200B is extra high molecular weight high density polyethylene blow molding grade which is recommended for 20-120 litre drums. It has excellent processability and exhibits very high impact strength, stiffness and extremely environment stress crack resistance.

Typical Applications: Hazardous chemical drums, Agricultural chemical drums.

Typical Properties:

Properties	HD7200B	Unit	Test Method
Physical Properties			
Melt Flow Rate (2.16 kg/190 °C)	0.05	g/10 min	ASTM D1238
Melt Flow Rate (21.6 kg/190°C)	8.5	g/10 min	ASTM D1283
Density	0.956	g/cm ³	ASTM D1505
Vicat Softening Point @ 10 N, 50 °C/hr	124	°C	ASTM D1525
Melting Point	134	°C	ASTM D3418
Mechanical Properties (Based on compression specimens)			
Tensile Strength @ Yield	300	kg/cm ²	ASTM D638
Tensile Strength @ Break	350	kg/cm ²	ASTM D638
Elongation @ Break	800	%	ASTM D638
Stiffness	10000	kg/cm ²	ASTM D747
Flexural Modulus	12000	kg/cm ²	ASTM D790
Notched Izod Impact Strength	25 (NB)*	kg.cm/cm	ASTM D256
Durometer Hardness	63	Shore D	ASTM D2240
ESCR, F50 (Condition B, 25 % Igepal)	>1000	hrs	ASTM D1693

NB = Non Break

Note: Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.

Revised Date: Oct. 2021





HD7200B

High Density Polyethylene Resin

Processing Condition:

Extruder temperature: 195 - 220 °C Die temperature: 200 - 220 °C

FDA Statement:

HDPE under the brand InnoPlus complies with U.S. FDA 21 CFR 177.1520 (c) (2.1) and (2.2) regulation for polyethylene used in articles that contact food suitable for articles used for packaging or holding food during cooking.

Disclaimer:

This Applications specified herein is for reference only and not suitable for using in the manufacturing of any products in medical and pharmaceutical sectors.

- Determination of suitability of the product for the use and purpose shall be the customer's responsibility. Customer is obligated to inspect and test the product for such suitability. Customer is responsible for appropriate, safe, legal use processing and handling of the product.
- ate
 given by us. To our best knowledge, information contained herein is true and accurate as of the date of its publication. However, we make no representations or warranties with respect to accuracy, reliability and completeness of the information contained herein for any purpose.
- No warranties, express or implied, which extend beyond the description herein are given by us. Nothing herein shall constitute any implied warranty of merchantability or fitness for

Note: Properties reported here are typical values of the product, not to be considered as specifications. PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.